MountFilm HighTack ASLAN DK 3

Double-sided self-adhesive film, permanent | permanent

Double-sided self-adhesive film, suitable to turn maps, prints, plans, posters and more into self-adhesive substrates. Liner and permanent adhesive on both sides, reduced initial tack on one side, pH-neutral adhesive.

For additional information please contact our technical advisory service:

+49 (0) 22 04. 7 08-80

Construction

face-film: soft PVC, transparent

thickness: $\sim 70 \, \mu m$

adhesive: acrylic pressure adhesive

> square quantity: ~ 25 g/m² side with paper release liner side with plastic release liner square quantity: ~ 30 g/m²

release liner: silicone paper square weight: ~ 67 g/m²

siliconised LDPE-film square weight: ~ 63 g/m²

Characteristics

adhesive strength: side with paper-covering (ASTMD-903)

permanent, with low initial tack

immediately: ~ 4 N/25 mm ~ 10 N/25 mm after 1 week:

side with plastic-covering

permanent, with extra strong adhesive strength

immediately: ~ 10 N/25 mm after 1 week: ~ 20 N/25 mm

tensile strength: DIN 53 455 longitudinal: ~ 150%

lateral: ~ 130%

temperature: application temperature: min. 15°C

service temperature range: -30 °C up to +80 °C

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany **phone** +49 (0) 2204.708 80 · **fax** +49 (0) 2204.708 50 e-mail info@ASLAN-Schwarz.com









MountFilm HighTack ASLAN DK 3

Processing

application:

Dry application only.

storage life:

Before application the foils can be stored for minimum 3 years from date of production. The film must be stored at room temperature $(15-25\ ^{\circ}C)$ and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed `hanging´ racks.

State: 03|2015

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany **phone** +49 (0) 2204.708 80 · **fax** +49 (0) 2204.708 50 **e-mail** info@ASLAN-Schwarz.com







